

PROLITE® TILE & STONE MORTAR

- High flexibility and bond strength
- Bonds large format tile and stone
- Non-slip for wall applications
- Non-slump for floor applications
- Use as a thin-set or medium-bed mortar, up to 3/4" (19 mm) thick on floors
- 30 lb. (13.6 kg) bag covers same area as a typical 50 lb. (22.68 kg) bag
- Contributes to LEED certification

PRODUCT DESCRIPTION

ProLite® Tile & Stone Mortar offers high flexibility and bond strength for a wide variety of floor and wall tile installations. It can be applied 3/4" thick on horizontal surfaces. Excellent for setting large format tile or stone, ProLite will not sag or slip on walls and offers non-slump performance for floor installations. Formulated with CustomLite® Technology, ProLite is 40% lighter than traditional mortars, providing excellent handling characteristics. A 30 lb. bag covers the same area as a 50 lb. bag of traditional mortar. Formulated with recycled material – contributes to LEED certification. Protected with MoldGard® Technology to resist mold and mildew growth. Exceeds ANSI A118.4 and A118.11 without the need for additives.

USES — TILE TYPES

- Vitreous, semi-vitreous or absorptive tile: Ceramic, mosaic, quarry, cement, impervious porcelain and glass mosaic tile
- Brick and mini-brick
- Precast terrazzo
- Natural stone tile

AREAS OF USE

- Interior or exterior floors, countertops, walls
- Concrete, mortar beds, masonry, Portland cement plaster
- Backerboards such as WonderBoard® and EasyBoard®
- Exterior grade plywood (interior residential and light commercial dry areas)
- Gypsum wall board (dry areas)
- Waterproofing membranes such as RedGard® Waterproofing and Crack Prevention Membrane or Custom® 9240 Waterproofing and Anti-Fracture Membrane; liquid applied and sheet membranes



CUSTOM®
BUILDING PRODUCTS

PRICE



- Water-resistant wallboard
- Existing ceramic tile
- Sheet vinyl flooring, VCT
- Plastic laminates
- Cutback adhesive

LIMITATIONS

- Do not bond directly to hardwood, Luan plywood, particle board, parquet, cushion or sponge-back vinyl flooring, metal, fiberglass, plastic and OSB panels.
- When setting moisture sensitive stone, tile or agglomerates use 100% Solids Epoxy Mortar.
- Do not use to install resin-backed stone.
- When setting dimensional stone larger than 12" x 12" (30 x 30 cm), contact Technical Services for recommendations regarding subfloor deflection requirements.

SURFACE PREPARATION

General Surface Preparation:

Surfaces must be structurally sound, clean, dry and free from grease, oil, dirt, curing compounds, sealers, adhesives or any other contaminant that would prevent a good bond. Glossy or painted surfaces must be sanded, stripped and cleaned of waxes, dirt or any contaminants. Ambient temperature, surfaces and materials should be maintained at a temperature above 50° F (10° C) or below 100° F (38° C) for 72 hours.

Cementitious Surfaces:

Concrete or plaster must be fully cured and accept water penetration. Test by sprinkling water on various areas of the substrate. If water penetrates, then a good bond can be achieved. If water beads, surface contaminants are present and loss of adhesion may occur. The contaminants should be removed before installation. Concrete must be free of efflorescence and not subject to hydrostatic pressure. Concrete slabs should have a broomed or brushed finish to enhance the bond. Smooth concrete slabs must be roughened to ensure a good bond.

Plywood Substrates:

Plywood floors including those under resilient flooring must be built to industry standards. For questions about proper subfloor installation, call Technical Services.

Backerboards and Underlayments:

Tile backerboards such as WonderBoard® and EasyBoard® are a superior alternative to using a second layer of plywood as a final substrate for tile installation. EasyMat™ is an underlayment that can be used in the same regard. Each provide unique benefits to tile installation but all can be installed over plywood to ensure that maximum bond strengths and performance are achieved. Refer to respective data sheet for installation information.

Existing Ceramic Tile, Resilient Flooring or Plastic Laminates:

Adhesive layers must be removed as they reduce mortar bond strength to cement surfaces. Use extreme caution as adhesives may contain asbestos fibers. Do not sand or grind adhesive residue, as harmful dust may result. Never use adhesive removers or solvents, as they soften the adhesive and may cause it to penetrate into the concrete. Adhesive residue must be wet-scraped to the finished surface of the concrete, leaving only the transparent staining from the glue. Do a test bond area first, to determine desirable results. Refer to the RFCI Pamphlet, "Recommended Work Practices for Removal of Resilient Floor Coverings" for further information.

Expansion Joints:

Expansion joints, control joints and cold joints should never be bridged with setting material. They must be brought through the tile work and filled with an appropriate elastomeric sealant.

Cutback Adhesive over Concrete:

Adhesive layers must be removed as they reduce mortar bond strength to cement surfaces. Use extreme caution as adhesives may contain asbestos fibers. Do not sand or grind adhesive residue, as harmful dust may result. Never use adhesive removers or solvents, as they soften the adhesive and may cause it to penetrate into the concrete. Adhesive residue must be wet-scraped to the finished surface of the concrete, leaving only the transparent staining from the glue. Do a test bond area first, to determine desirable results. Refer to the RFCI Pamphlet, "Recommended Work Practices for Removal of Resilient Floor Coverings" for further information.

MIXING

Thoroughly mix 7 - 7.5 quarts (6.62 - 7.1 L) clean, cool water and 30 lb. (13.6 kg) ProLite together to a smooth, paste consistency. Mix by hand or use a low speed (150 - 200 RPM) 1/2" (13 mm) drill. Let slake or stand 5 - 10 minutes, stir again and use. Stir occasionally to keep fluffy, but do not add more water. When properly mixed, troweled ridges will stand with no slump.

APPLICATION

INSTALLATION TO CONFORM TO ANSI A108.5. Use proper sized notched trowel to ensure 100% coverage under tiles. Using flat side of trowel, apply skim coat of mortar to the surface. Apply additional mortar with notched side of trowel held at a 45° angle to the surface, combing in one direction. Press tile firmly into place in a perpendicular motion across ridges, moving back and forth. Perpendicular pressing flattens ridges and closes valleys allowing maximum coverage. With some tile, back buttering is advisable. Adjust tile promptly and beat in with block and rubber mallet. Use as a thin-set or medium bed mortar — can be applied up to 3/4" (19 mm) thick after beat in. Periodically pull up a tile and check the back to ensure complete coverage with the adhesive. Do not spread more material than can be tiled in 15 minutes or while material has wet tack (sticky to the touch). If material has skinned over (not sticky), recomb with notched trowel. If too dry, remove and replace with fresh material. Material in bucket will remain workable in excess of 4 hours.

CURING

Allow to cure for 24 hours before grouting or light traffic, depending upon temperature and humidity. Polyblend® or Prism® SureColor® Grout is recommended.

COVERAGE

SQUARE FOOT COVERAGE PER 30 LB. BAG (SQUARE METER PER 13.6 KG)	
TROWEL SIZE	COVERAGE
1/4" x 1/4" x 1/4" Square-Notch (6 x 6 x 6 mm)	90 - 100 sq. ft. (8.4 - 9.3 m ²)
1/4" x 3/8" x 1/4" Square-Notch (6 x 9 x 6 mm)	63 - 70 sq. ft. (5.6 - 6.5 m ²)
1/2" x 1/2" x 1/2" Square-Notch (13 x 13 x 13 mm)	45 - 50 sq. ft. (4.2 - 4.6 m ²)
3/4" x 9/16" x 3/8" U-Notch (19 x 14 x 9 mm)	36 - 40 sq. ft. (3.3 - 3.7 m ²)

CLEAN-UP

Clean with water before material dries.

STORAGE

Store in a cool dry area.

SAFETY

Contains Portland cement. Avoid eye contact or prolonged contact with skin. Wash thoroughly after handling. If eye contact occurs, flush with water for 15 minutes and consult a physician. This product contains free silica. Do not breathe dust; wear NIOSH approved respirator.

ORDERING INFORMATION

	ITEM CODE	SIZE	COLOR	PACKAGE
USA	PLMG30	30 lb. (13.6 kg)	Gray	Bag
USA	PLMW30	30 lb. (13.6 kg)	White	Bag
Canada	CPLMG30	30 lb. (13.6 kg)	Gray	Bag

TECHNICAL DATA

Exceeds ANSI A118.4 and A118.11 specifications.

	PROLITE® TILE & STONE MORTAR
Pot Life	4 hours
Open Time	55 - 60 minutes
Shear Bond:	
Bisque Tile 28 Days	600 psi (42.2 kg/cm ²)
Porcelain Tile 28 Days	450 psi (31.6 kg/cm ²)
Quarry Tile to Plywood 28 Days	250 psi (17.6 kg/cm ²)

LIMITED WARRANTY

Custom Building Products ("Custom") warrants to the original consumer purchaser that its product shall be free from defects in material and workmanship under normal and proper usage for a period of one year following the date of original purchase. Custom's sole liability under this warranty shall be limited to the replacement of the product. Some states do not allow the exclusion or limitation of incidental or consequential damages, so the above limitation or exclusion may not apply to you. This warranty will not extend to any product which has been modified in any way or which has not been used in accordance with Custom's printed instructions. Custom makes no other warranties either express or implied. This warranty gives you specific legal rights, and you may have other rights that vary from state to state.



CUSTOM[®]
BUILDING PRODUCTS